

# **FinoPAC**

### CT Corrosion Inhibitor

## **Description**

FinoPAC is comprised of combinatorial chemistry consisting of filming amines, quaternary ammonium compounds and oxygen scavenger. It is a multifunctional additive that functions as corrosion inhibitor, bactericide, and oxygen scavenger and designed for use in coiled tubing fluids, workover fluids, packer fluids and completions fluids. FinoPAC performs as a corrosion inhibitor by preferentially adsorbing a thin molecular film on all metal surfaces, thereby stifling the corrosion process.

## **Typical Physical Properties**

Characteristic	Specification
Appearance	Dark liquid
Active	20%
Density	~8.5 lbs per ga
Flash Point	> 200°F
Pour Point	25°F
Solubility	Water and Methanol

### **Applications**

FinoPAC is also available as a concentrate which can be diluted 4 times in water. It can also be diluted in alcohol/water or alcohol/glycol if required. FinoPAC is typically batch treated at a rate of ½ to 1½ gallons per 10 barrels.

#### **Packaging**

FinoPAC is available in 55 gallons drums, 275 or 330 gallon totes.

#### Handling

Please refer to the Safety Data Sheet for further handling information.

#### Availability

Global from Houston, TX-USA, Midland, TX-USA, Dubai, UAE, and Bombay, India.

#### **Performance Data**

Corrosion tests were performed with FinoPAC using 1018 steel coupon, under saturated CO<sub>2</sub> environment for 24 hours at 280°F. The brines tested were 9.3 ppg NaCl and 10.5 ppg CaCl<sub>2</sub>. The data are shown in Tables 1 and 2 and Figures 1 through 8. The corrosion data does not look good because the tests were performed under very harsh conditions (saturated CO<sub>2</sub>). It is highly unlikely the CT or packer fluids would be saturated with CO<sub>2</sub>. Under normal packer fluid environment, FinoPAC should perform better.



#### **Performance Data**

Corrosion tests were performed with FinoPAC using 1018 steel coupon, under saturated CO<sub>2</sub> environment for 24 hours at 280°F. The brines tested were 9.3 ppg NaCl and 10.5 ppg CaCl<sub>2</sub>. The data are shown in Tables 1 and 2 and Figures 1 through 8. The corrosion data does not look good because the tests were performed under very harsh conditions (saturated CO<sub>2</sub>). It is highly unlikely the CT or packer fluids would be saturated with CO<sub>2</sub>. Under normal packer fluid environment, FinoPAC should perform better

Characteristic	Specification
Appearance	Dark liquid
Active	20%
Density	~8.5 lbs per ga
Flash Point	> 200°F
Pour Point	25°F
Solubility	Water and Methanol

Characteristic	Specification
Appearance	Dark liquid
Active	20%
Density	~8.5 lbs per ga
Flash Point	> 200°F
Pour Point	25°F
Solubility	Water and Methanol



Figure 1. 10.5 ppg CaCl<sub>2</sub> with and without FinoPAC





Figure 2. 9.3 ppg NaCl without and with FinoPAC